

Appl. No. 10/620,928
Amdt. Dated August 6, 2004
Office Action Date April 6, 2004

Amendments to the Specification:

On page 4 please replace the last full paragraph with the following:

--Polymerization reaction is continued until the conversion of monomer mixture reaches at least 90%. The resulting aqueous latex is solidified by a salt-acid solidification process, a process using a salt such as calcium chloride, magnesium sulfate, sodium sulfate or ammonium sulfate a process using a ~~bron~~ boron compound such as boric acid, borax, etc., a heat solidification process, a freeze solidification process, etc. and the resulting copolymers ~~is~~ are fully washed with water and dried. The resulting elastomer has a Mooney viscosity LM_{1+4} (100°C) of about 10 to about 100, preferably about 20 to about 80.--

On page 8, please replace the first full paragraph with the following:

--Sulpheneamide Sulfenamide compound includes those usually used as a vulcanization ~~vulcanization~~ accelerator such as N-cyclohexyl-2-benzoyl ~~sulpheneamide~~, sulfenamide, N-t-butyl-2-benzothiazolyl ~~sulpheneamide~~, sulfenamide, N-oxydiethylene-2-benzothiazolyl ~~sulpheneamide~~, sulfenamide, N,N-dicyclohexyl-2-benzothiazolyl ~~sulpheneamide~~, sulfenamide, etc., at least on of which can be used.--